

Suitability for outdoor use of different combinations between polyurethane Decoral System® Powder coatings and heat transfer film Decoral System® must be assessed on www.decoral-system.com. (link: **TESTED FOR OUTDOOR USE**) or contacting our laboratory.

New Millennium 3D



Powder Coating: DS-0418S + Heat Transfer Film: 2117/01



Powder Coating: DS 721 + Heat Transfer Film: 2117/02



Powder Coating: DS-0733S + Heat Transfer Film: 2117/03



Powder Coating: DS 733 + Heat Transfer Film: 2117/12




Powder Coating: 8G-096-A009 + Heat Transfer Film: 2117/13





Powder Coating: DS 752 + Heat Transfer Film: 2117/23


L' idoneità all'impiego in esterno degli abbinamenti tra prodotti vernicianti poliuretanici Decoral System® e film sublimatici Decoral System® dovrà essere valutata sul sito internet www.decoral-system.com (alla voce **FINITURE ADATTE PER USO ESTERNO**) oppure contattando il nostro laboratorio.


New Millennium 3D


Test Report: Florida Natural Exposure		Decoral LAB Research and Development	157
Florida Test	Total duration: 12 months		
EXPOSURE PERIOD: FROM: 10/08/2022 TO: 10/08/2023			
LAB ID NUMBER: 50704 POWDER COATING: RG-096-0009 HEAT TRANSFER FILM: 2117/15 colour variation (ΔE): 1,56 residual gloss: 69%			
Technical Remarks Good residual gloss and normal color variation (ΔE)			
Technical Opinion: Suitable for OUTDOOR USE			
Test was carried on samples prepared according to technical specifications supplied by new materials manufacturers. REQUIREMENTS The residual gloss must be at least 50% of the original gloss. The final evaluation will be based on visual inspection with the naked eye			
Mod_TR_02_rev02 Laboratory Decoral System Date: 05/12/2023 ID Report: TR-NE-157-2023			

Test Report: Florida Natural Exposure		Decoral LAB Research and Development	298
Florida Test	Total duration: 12 months		
EXPOSURE PERIOD: FROM: 10/08/2022 TO: 10/08/2023			
LAB ID NUMBER: 52706 POWDER COATING: ES-782 HEAT TRANSFER FILM: 2117/25 colour variation (ΔE): 1,05 residual gloss: 86%			
Technical Remarks Good residual gloss and normal color variation (ΔE)			
Technical Opinion: Suitable for OUTDOOR USE			
Test was carried on samples prepared according to technical specifications supplied by new materials manufacturers. REQUIREMENTS The residual gloss must be at least 50% of the original gloss. The final evaluation will be based on visual inspection with the naked eye			
Mod_TR_02_rev02 Laboratory Decoral System Date: 08/02/2024 ID Report: TR-NE-298-2024			

Test Report: Florida Natural Exposure		Decoral LAB Research and Development	154
Florida Test	Total duration: 12 months		
EXPOSURE PERIOD: FROM: 23/05/2014 TO: 27/05/2015			
LAB ID NUMBER: 94014 POWDER COATING: ES-723 HEAT TRANSFER FILM: 2117/02 Colour variation (ΔE): 1,97 residual gloss: 86%			
Technical Remarks Excellent residual gloss and low colour variation (ΔE)			
Technical Opinion: Suitable for OUTDOOR USE			
Test was carried on samples prepared according to technical specifications supplied by new materials manufacturers. REQUIREMENTS The residual gloss must be at least 50% of the original gloss. The final evaluation will be based on visual inspection with the naked eye			
Mod_TR_02_rev02 Laboratory Decoral System Date: 19/10/2015 ID Report: TR-NE-154-2015			

Test Report: Florida Natural Exposure		Decoral LAB Research and Development	177
Florida Test	Total duration: 12 months		
EXPOSURE PERIOD: FROM: 20/08/2013 TO: 21/08/2014			
LAB ID NUMBER: 32071 POWDER COATING: D9-06183 HEAT TRANSFER FILM: 2117/01 Colour variation (ΔE): 1,47 residual gloss: 99%			
Technical Remarks Excellent residual gloss and low colour variation (ΔE)			
Technical Opinion: Suitable for OUTDOOR USE			
Test was carried on samples prepared according to technical specifications supplied by new materials manufacturers. REQUIREMENTS The residual gloss must be at least 50% of the original gloss. The final evaluation will be based on visual inspection with the naked eye			
Mod_TR_02_rev02 Laboratory Decoral System Date: 18/11/2014 ID Report: TR-NE-177-2014			

Test Report: Florida Natural Exposure		Decoral LAB Research and Development	150
Florida Test	Total duration: 12 months		
EXPOSURE PERIOD: FROM: 10/08/2022 TO: 10/08/2023			
LAB ID NUMBER: 51276 POWDER COATING: D9-07393 HEAT TRANSFER FILM: 2117/05 colour variation (ΔE): 1,47 residual gloss: 81%			
Technical Remarks Good residual gloss and normal color variation (ΔE)			
Technical Opinion: Suitable for OUTDOOR USE			
Test was carried on samples prepared according to technical specifications supplied by new materials manufacturers. REQUIREMENTS The residual gloss must be at least 50% of the original gloss. The final evaluation will be based on visual inspection with the naked eye			
Mod_TR_02_rev02 Laboratory Decoral System Date: 05/12/2023 ID Report: TR-NE-150-2023			

Test Report: Florida Natural Exposure		Decoral LAB Research and Development	106
Florida Test	Total duration: 12 months		
EXPOSURE PERIOD: FROM: 27/04/2019 TO: 07/05/2020			
LAB ID NUMBER: 46265 POWDER COATING: D9-735 HEAT TRANSFER FILM: 2117/12 Colour variation (ΔE): 2,15 residual gloss: 79%			
Technical Remarks Good residual gloss and normal colour variation (ΔE)			
Technical Opinion: Suitable for OUTDOOR USE			
Test was carried on samples prepared according to technical specifications supplied by new materials manufacturers. REQUIREMENTS The residual gloss must be at least 50% of the original gloss. The final evaluation will be based on visual inspection with the naked eye			
Mod_TR_02_rev02 Laboratory Decoral System Date: 27/10/2020 ID Report: TR-NE-106-2020			